


Baunit StarTex Grob / CeramicTex

Non-slip, alkali-resistant textile glass fibre mesh



- Prevents cracks
- Highly alkali-resistant
- Coarse fabric structure

Product Overview Slip-resistant, alkali-resistant textile glass fibre mesh for embedding into Baunit reinforcement coats for heavy duty applications, system-tested.

Composition Textile glass with special finish for sliding resistance / dimensional stability and alkali resistance.

Properties

- Slide-proof
- Alkali resistant
- System component of the Baunit external thermal insulation composition systems

Application For heavy duty reinforcement on cracked old render facade and for reinforcing render systems. Lay the Baunit StarTex Grob / CeramicTex mesh wet-in-wet into the reinforcement basecoat render ensuring it is free from bubbles or folds. position so that it lies within the upper third of the thickness of the reinforcement coat. Do not cut on the roll.

Technical Data

Mass per Unit Area:	$\geq 200 \text{ g/m}^2$
Mesh size:	$6.5 \times 7 (\pm 0,5 \text{ mm Tolerance})$ approx.
Tear Strength:	2.2 - 2.5 kN/5cm
Tear Strength:	1.2 - 1.3 kN/5cm (28 days after ETAG)

	StarTex Grob / CeramicTex
yield	app. 45 m ² /roll
Consumption	app. 1.1 m ² /m ²

Delivery Format Roll:50m2 (Width 1m), Pallet = 20 Rolls = 1,000 m²

Storage StarTex Grob / CeramicTex should be stored under normal climactic conditions. It should not be unusually dry nor unusually frozen for application. Ensure that StarTex Grob/CeramicTex is stored so that it cannot be misshapen. Misshapen or damaged StarTex Grob/ CeramicTex cannot be used.

Quality Assurance Internal quality assurance is provided by the manufacturer's plant.

Substrate Ensure there is sufficient key in the basecoat material before laying on the StarTex Grob / CeramicTex.

Processing Position so that it lies within the upper third of the thicknes of the basecoat.

Notes and General Information Take note of the technical datasheets of the respective adhesive and reinforcing coat renders. If you need further information about this material or its handling, consult with our outside service experts about the details and the materials.

Written and oral application technology recommendations provided by us to assist the seller/processor are based on our experience and reflect the current state of the art in science and practical application know-how. However, it is understood that these recommendations are non-binding. They do not create any legal relationship or any ancillary obligations in connection with the sale contract. They do not release the buyer from its obligation to verify the suitability to our products for the intended purpose or use by itself.